








CIIR

B 1743

- 
- 
- 
- 
- 
- 
- 

- Hardness [Shore A]: 60 ±5
- Density [g/cm³]: 1.11
- Tensile strength [N/mm²]: 13
- Elongation at break [%]: 600
- Ozone resistance: resistant
- Weather resistance: resistant
- Oil resistance: non resistant
- Benzine resistance: non resistant
- Acid resistance: good resistant
- Strong bases: good resistant
- Abrasion resistance: suitable

WORKING TEMPERATURE RANGE

Medium	dyn. (stat.)	max.	short-term
Air	-40 °C	+100 °C	+120 °C
Water	-	+110 °C	+130 °C

COMPRESSION SET DIN ISO 815

Duration	Temperature	CS
22 h	100 °C	40 %

AGEING DIN 53508

Conditions	Hardness	Strength	Elongation
70h/100 °C	+5 Shore A	±5 %	-15 %

gumex

... příznivé partnerství

ROTA-CURED-SHEETS

Article-number	Thickness mm	Width m	Length m	Surface	No. of insert.
4011 69100	1.0	1.4	20	S S	0
4011 69150	1.5	1.4	20	S S	0
4011 69200	2.0	1.4	20	S S	0
4011 69300	3.0	1.4	10	S S	0
4011 69400	4.0	1.4	10	S S	0
4011 69500	5.0	1.4	10	S S	0
4011 69600	6.0	1.4	10	S S	0
4011 69800	8.0	1.4	5	S S	0

PRESS-CURED-SHEETS

Article-number	Thickness mm	Width m	Length m	Surface	No. of insert.
4213 69100	10.0	1.4	5	S S	0

S = smooth

Please Note:

This catalogue has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operation conditions influence the application of each product, the information supplied in this catalogue can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether specified properties of our products are sufficient for the intended use. If there is any doubt (e.g. chemical resistance), do not hesitate to contact our qualified engineers. The use of our products is at the user's own risk. We do not have any influence concerning the application and individual usage. We do of course guarantee the quality of our products according to our general sales conditions, available on request.

22.8.2003

Subject to alteration without prior notice - All mentioned properties contained in this catalogue are guiding values representing longterm experience average.

Semperit Technische Produkte Gesellschaft m.b.H. & Co KG
 A-2632 Wimpassing, Triester Bundesstraße 26
 Telefon +43 2630 310-0*, Telefax +43 2630 310 320
 E-Mail: semperflex@semperit.at, Internet: www.semperit.at

semperflex 
 A MEMBER OF THE SEMPERIT-GROUP