



**ZAKŁADY CHEMICZNE  
SPÓŁDZIELNIA PRACY  
W GOLENIOWIE  
POLAND**

**CARD OF TECHNICAL PARAMETERS**

**PRODUCT: RUBBER PACKING SHEET NR-L RED GB**

| PROPERTIES  | QUANTITY/UNIT          | TESTING METHODS         |
|---|------------------------|-------------------------|
| Hardness (H)  | 55±5°ShA               | PN-C-04238:1980         |
| Tensile strength (TS <sub>b</sub> ) min   | 5 MPa                  | PN-ISO 37:2007/AC1:2008 |
| Relative elongation at break (E <sub>b</sub> ) min  | 400%                   | PN-ISO 37:2007/AC1:2008 |
| Compression set at temp. 70°C after 24 hrs<br>(ε <sub>ct</sub> ) max  | 40%                    | PN-ISO 815:1998         |
| Resistance to heat ageing in the air at temp. 70°C<br>after 144 hrs (SC)<br>ΔTS <sub>b</sub><br>ΔE <sub>b</sub><br>ΔH | ±30<br>-50<br>±10      | PN-ISO 188:2000         |
| Fragility temperature (T <sub>k</sub> )   | -35°C                  | PN-ISO 812:1999         |
| Density (ρ) max   | 1,45 Mg/m <sup>3</sup> | PN-ISO 2781+AC1:1996    |

Zakłady Chemiczne Spółdzielnia Pracy 72-100 Goleniów ul. I Brygady Legionów 1/3  
e-mail: sprzedaz@gumagoleniow.pl  
www.gumagoleniow.pl