


# CR

## CR N 572



### General:

**CR**, black, high-grade  
Sulphur crosslinked  
Resistant to most aliphatic oils  
Nonresistant against aromatic oils  
Self-extinguishing according to ISO 4589-2: 2017, O<sub>2</sub> Index up to 30%  
(depending on the thickness and the shape of the specimen)

Wrapping: stretched foil, labelled  
standard finishing in separation foil

\*SVHC < 0,1%. Note: for consumer articles with skin contact further restrictions apply according to REACH.

### Working temperature range

Medium	dyn.(stat.)	max.	short-term
Air Water oil	-20 (-40)°C	+90°C +70°C +80°C	+120°C +90°C +100°C

### Compression set DIN ISO 815 <sup>\*)</sup>

Duration	Temperature	CS
22h	+70°C	35%

### Ageing ISO 188 <sup>\*)</sup>

Conditions	Hardness	Strength	Elongation
70h / 70°C	5 Shore A	5 %	15 %

### Swelling ISO 1817 <sup>\*)</sup>

Medium	Conditions	Hardness	Volume
IRM 901	70h / 100°C	5 Shore A	10 %

### Properties:

Hardness [Shore A]:	ISO 48-4	<sup>*)</sup>	70±5
Density [g/cm <sup>3</sup> ]:	ISO 1183-1	<sup>*)</sup>	~1,55
Tensile Strength [N/mm <sup>2</sup> ]:	ISO 37 type 2	<sup>*)</sup>	7
Elongation at Break [%]:	ISO 37 type 2	<sup>*)</sup>	300

correspond to WDK-guideline 2201 : 2020-10 "Quality characteristics of Elastomer sheets and plates"

### Stabilities:

Ozone resistance:	resistant
Weather resistance:	good resistant
Oil resistance:	resistant – no aromatic oils
Fuel resistance:	moderately resistant
(only alcohol-free fuels!)	
Acid resistance:	resistant
Strong bases:	resistant
Abrasion resistance:	moderately resistant

ROTA-SHEETS Product number	thickness (in mm)	width (in mm)	length (in mm)
401126100	1,0	1.400	20.000
401126200	2,0	1.400	20.000
401126300	3,0	1.400	10.000
401126400	4,0	1.400	10.000
401126500	5,0	1.400	10.000
401126600	6,0	1.400	10.000
401126800	8,0	1.400	5.000
401126000	10,0	1.400	5.000

PRESS-SHEETS Product number	thickness (in mm)	width (in mm)	length (in mm)
421326120	12,0	1.400	5.000
421326150	15,0	1.400	5.000
421326200	20,0	1.400	5.000
421325000	25,0	1.400	5.000
421326300	30,0	1.400	5.000
421326400	40,0	1.400	5.000
421326500	50,0	1.400	5.000

#### PAH disclaimer:

Referring to an international proficiency test and information received from the testing laboratories about accuracy of test results we may inform you, that test results for the same specimen from different laboratories may not correlate:

\* Results of the 10 PAH with individual limits of < 1 mg/kg in the measurement range around the limit are only accurate to approx. ± 70%.

\* Results of the overall limit of < 50 mg/kg are only accurate to approx. ± 35%

Our test results are provided on an as-is basis and to the best of our knowledge, without any legally binding commitment. Our tests do not release you from own tests as to the respective application envisaged.

\*SVHC < 0,1%. Note: for consumer articles with skin contact further restrictions apply according to REACH.

#### <sup>\*)</sup> Please note:

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. This data sheet has been carefully prepared in order to provide our customers with the best possible advice. The information, figures, calculations, test values and data provided correspond to the current state of the art and represent the average result of a sufficient number of tests and trials.. As individual operation conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether specified properties of our products are sufficient for the intended use. If there is any doubt (e.g. chemical resistance), do not hesitate to contact our qualified engineers. The use of our products is at the user's own risk. We do not have any influence concerning the application and individual usage. We do of course warrant the quality of our products according to our General Sales Conditions. available on our website or

Subject to alteration without prior notice: In order to always have the latest product- and safety information make sure you visit our website ([www.semperitgroup.com](http://www.semperitgroup.com)) regularly or contact specialist dealers or a Semperit application engineer. Additional important general information about the range, storage and tolerances can also be found at our website ([www.semperitgroup.com](http://www.semperitgroup.com)) and must be followed without exception.

certified according to ISO 9001:2015, ISO 45001:2018, ISO 14001:2015

Date: 2025-08-18 SEMPERIT Datasheet DP-EN-CRN572-v3