



ARPLANK 45 contains **30%** of recycled content coming from PCR (post-consumer recycled) polyethylene and recycled ARPLANK.

Physical properties

	Test method	Typical result
Length (mm)	ISO 1923	≥ 2,000
Width (mm)	ISO 1923	≥ 1,200
Thickness (mm)	ISO 1923	≥ 150
Density (kg/m ³)	ISO 845	45
Compressive strength 25% strain (kPa) 50% strain (kPa)	ISO 7214	120 200
Tensile strength (kPa) Tensile elongation (%)	ISO 7214	550 60
Compression set Stabilising 30min (%) Stabilising 24h (%)	ISO 7214 25% - 22h loading	14 4
Compression set Stabilising 30min (%) Stabilising 24h (%)	ISO 7214 50% - 22h loading	35 5
Tear strength (N/cm)	ISO 8067-B	40
Hardness Shore 00	ISO 868	72
Water absorption	DIN 53428	< 1
Thermal conductivity (W/(m.K)) Test temperature 10°C Test temperature 23°C	ISO 8301	0.042 0.043
Service temperature (°C)	Internal	100
Flammability	FMVSS302 (Burn rate <100mm/min)	Pass

Version 04

This information is provided as a convenience to customers and reflects the results of internal tests conducted on ARPLANK samples. While all reasonable care has been taken to ensure that this information is accurate as of the date of issue, JSP does not represent, warrant or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability or completeness of the information. ARPLANK is a registered trade mark.